

IMPORTACIONES YARNABETH

Item			
Specification	20s/2	40s/3	20s/3
Tex	60	45	90
Type of Fiber	Staple fiber	Staple fiber	Staple fiber
Single End Breaking Strength / CN	1860	1360	2800
Single End Breaking Strength / CV%	9,5%	10,0%	9,0%
Elongation at Break	16- 22%	16 - 22%	17 - 23%
Colour deviation class	4 ~ 5	4 ~ 5	4 ~ 5
Different Colour deviation class	3 ~ 4	3 ~ 4	3 ~ 4
Colour fastness to washing $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Colour fastness to organic solvents $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Colour fastness to rubbing (dry) $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Colour fastness to rubbing (wet) $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Lubricate rate	5%	5%	5%
Length range	$\pm 2\%$	$\pm 2\%$	$\pm 2\%$

IMPORTACIONES YARNABETH			
Artículo	Hilo de coser 100% poliéster hilado Especificación		
Especificación	20s/2	40s/3	20s/3
Tex	60	45	90
Tipo de fibra Fibra	Fibra	Fibra	Fibra
Resistencia a la rotura de un solo extremo / CN	1860	1360	2800
Resistencia a la rotura de un solo extremo / CV%	0,095	0,1	0,09
Alargamiento a la rotura	16- 22%	16 - 22%	17 - 23%
Clase de desviación de color	4 ~ 5	4 ~ 5	4 ~ 5
Diferente clase de desviación de color	3~ 4	3 ~ 4	3 ~ 4
Solidez del color al lavado $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Solidez del color a disolventes orgánicos $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Solidez del color al frote (seco)	3 ~ 4	3 ~ 4	3 ~ 4
Solidez del color al frote (húmedo) $\geq$	3 ~ 4	3 ~ 4	3 ~ 4
Tasa de lubricación	0,05	0,05	0,05
Rango de longitud	$\pm 2\%$	$\pm 2\%$	$\pm 2\%$