

Importaciones Yarnnabeth Ltda.	
Recuento nominal/capa:	120D/2
Tipo de fibra	Polyester triangular
Resistencia a la rotura de un solo extremo CN $\geq$	1050
Resistencia a la rotura de un solo extremo (CV) $\leq$	5.00%
Alargamiento a la rotura	17-24%
Giro de capas (T / M)	500 (Z)
Rango de torsión (T / M)	480~520
Desviación de color (el mismo lote) clase	4 ~ 5
Desviación de color (el lote diferente) clase	4
Solidez del color al lavado $\geq$	4
Color adulator a disolventes orgánicos $\geq$	4
Solidez del color al frote (seco) $\geq$	4
Solidez del color al frote (húmedo) $\geq$	4
Rango de longitud promedio	$\pm 2\%$
Lubricante %	2

Importaciones Yarnnabeth Ltda.	
Nominal Count/Ply	120D/2
Type of Fiber	Polyester triangular
Single End Breaking Strength CN $\geq$	1050
Single End Breaking Strength (CV) $\leq$	5.00%
Elongation at Break	17-24%
Ply Twist (T/M)	500 (Z)
Twist range (T/M)	480~520
Colour deviation (The same lot) class	4 ~ 5
Colour deviation(The different lot) class	4
Colour fastness to washing $\geq$	4
Colour fawtness to organic solvents $\geq$	4
Colour fastness to rubbing (dry) $\geq$	4
Colour fastness to rubbing (wet) $\geq$	4
Average Length range	$\pm 2\%$
Lube %	2